



HOT-MELT STICKS



HOT MELT STICKS FOR GUNS

**Globomelt
11112**

- Yellowish grade
- Fast joining of paper and board material
- Viscosity (180C⁰) ca. 4000 mPas
- R&B ca. 105C⁰
- Open time: 8 - 12 sec
- Sticks diameter: 11,5 mm and 43 mm

Longer open time

**Globomelt
11113**

- White-translucent grade
- Multipurpose applications
- Viscosity (180C⁰) ca. 8500 mPas
- R&B ca. 85C⁰
- Open time: 25 - 30 sec
- Sticks diameter: 11,5 mm

Longer open time

**Globomelt
11118**

- Translucent grade
- Multipurpose applications
- Viscosity (180C⁰) ca. 9500 mPas
- R&B ca. 85C⁰
- Open time: 30 - 40 sec
- Sticks diameter: 43 mm